

RESEARCH ARTICLE

Open Access



Surface roughness and Streptococcus mutans adhesion on surface sealant agent coupled interim crown materials after dynamic loading

Eda Eslemmez Topcu¹ , Onur Şahin^{2*} , Ayşegül Köroğlu³ , Füsün Cömert⁴ and Burak Yılmaz^{5,6,7}

Abstract

Background: With the application of surface sealant agents, smooth surfaces can be achieved in a shorter time when compared with conventional polishing. However, studies on the performance of these agents against chewing forces are not many. The purpose of this study was to evaluate the surface roughness and Streptococcus mutans adhesion on surface sealant coupled interim prosthetic materials after chewing simulation.

Methods: One hundred and twelve specimens were fabricated from two poly(methyl methacrylate) (Tab 2000, Dentalon Plus) and two bis-acryl (Tempofit, Protemp 4) interim crown materials and divided into 4 groups (n = 7) according to applied surface treatment: conventional polishing (control) and 3 surface sealant (Palaseal, Optiglaze, Biscover) coupling methods. The surface roughness values (R_a) were measured with a profilometer before (R_{a0}) and after aging through dynamic loading in a multifunctional chewing simulator for 10,000 cycles at 50 N load combined with integral thermocycling (between 5 and 55 °C) (R_{a1}). Specimens were incubated with Streptococcus mutans suspension and the total number of adherent bacteria was calculated by multiplying the counted bacterial colonies with the dilution coefficient.

Results: Surface sealant agent application significantly decreased the surface roughness compared with conventionally polished specimens, except for Optiglaze or BisCover LV applied Protemp 4 and Palaseal or Biscover LV applied Tempofit. Surface roughness after dynamic loading showed a statistically significant increase in all groups, except for the control groups of Tab 2000 and Protemp 4. A positive correlation was found between surface roughness values of interim prosthodontic materials and the quantity of Streptococcus Mutans.

Conclusions: Even though surface sealant agent application significantly decreased the surface roughness compared with conventionally polished specimens, dynamic loading significantly increased the surface roughness of all surface sealant coupled materials. The R_a values of all test groups were higher than the plaque accumulation threshold (0.20 μm). Streptococcus mutans adhered more on rougher surfaces.

Keywords: Interim materials, Chewing simulator, Surface sealant agent, Surface roughness, Streptococcus mutans

Background

Interim crowns provide function, aesthetics, protection of the pulp, prevent undesired tooth movements and gingival growth [1]. They may also be used to improve occlusal relationships in patients with non-ideal

*Correspondence: sonurs60@hotmail.com

² Department of Prosthodontics, Faculty of Dentistry, Alanya Alaaddin Keykubat University, 07490 Antalya, Turkey
Full list of author information is available at the end of the article



© The Author(s) 2022. **Open Access** This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>. The Creative Commons Public Domain Dedication waiver (<http://creativecommons.org/publicdomain/zero/1.0/>) applies to the data made available in this article, unless otherwise stated in a credit line to the data.

occlusion, when the vertical dimension is planned to be altered before the delivery of permanent restoration, and to the gingival shape, size, and location [2].

Polyethyl methacrylate (PEMA), poly (methyl methacrylate) (PMMA), urethane dimethacrylate (UDMA), polyvinyl methacrylate (PVMA), bis-acryl composite resin, and composite resin can be used with direct and indirect techniques to fabricate interim crowns [1–4]. Acrylic-based and composite-based materials, which have been used for many years, are still the most commonly used interim crown materials [2, 5].

Smooth surfaces are essential on restorations for aesthetics and reduced plaque accumulation [6, 7]. Interim crowns should be biocompatible and have surface properties that prevent bacterial adhesion and discoloration. Several studies have indicated that increased surface roughness promoted the increase in bacterial adherence and plaque accumulation [7–17].

In order to minimize the surface roughness on dental materials, polishing is carried out in several stages in laboratory conditions or chairside. Recently, surface sealant agents have been developed by manufacturers as an alternative to conventional polishing methods. These agents with different matrix formulations such as bisphenol glycidyl methacrylate (BisGMA), trimethylene glycol dimethacrylate (TEGDMA), tetrahydrofurfuryl methacrylate (THFMA) and urethane dimethacrylate (UDMA) have been developed to overcome surface defects, wear, and staining [18–21].

Restorative materials are expected to have good mechanical and surface properties, wear resistance, aesthetic appearance and biocompatibility. To understand the clinical performance of materials and their lifetime, dynamic loading can be applied by using chewing simulators. Wear after dynamic loading can impair the surface integrity, aesthetic appearance, positional stability and maxillomandibular relationship. In addition, due to wear, many systemic, biological and mechanical problems may occur through inhalation or ingestion of released

monomer components or filler particles on material surface. In this context, the response of restorative materials to chewing simulation, certain loads and friction forces is crucial to investigate incidence of cracks and fractures, surface wear, and deterioration [22, 23]. Although it has been reported that surface sealant agents can provide smoother surfaces in a shorter time than conventional methods, studies on the condition of these agents after simulated chewing are lacking [18]. In addition, how different sealant agents interact with interim crown materials in varied compositions under loading is not known.

The present study aimed to evaluate the effect of different surface treatments on the surface roughness and *Streptococcus mutans* adherence on interim crown materials before and after dynamic loading in a multifunctional chewing simulator [24]. The first null hypothesis was that surface sealant agent coupling would not affect the surface roughness of interim crown materials. The second null hypothesis was that dynamic loading would not affect the surface roughness and *Streptococcus mutans* adherence on tested materials.

Methods

Specimen preparation and surface treatments

In the present study, two bis-acryl composite resin-based (Protempt 4 (Prt), Tempofit (Tmp)) and two auto-polymerized polymethyl methacrylate (Tab 2000 (Tab), Dentalon Plus (Dnt)) interim crown materials were evaluated. By using stainless steel molds, twenty-eight disc shaped (10 mm in diameter and 2 mm in thickness) specimens were prepared for each resin in accordance with the manufacturers' instructions and divided into 4 groups (n=7) for surface treatment procedures; conventional laboratory polishing (control) and application of 3 different surface sealant agents (Palaseal (Ps), Optiglaze (Og), Biscover LV (Bc)). Surface sealant agents and interim crown materials used in the present study are shown in Table 1.

The surfaces of all specimens were finished with a tungsten carbide bur (S274 190 060, Horico) and wet-ground

Table 1 Surface sealant and interim crown materials used

Product	Code	Component	Manufacturer
Palaseal	Ps	Methyl methacrylate, tris(2-hydroxyethyl)-isocyanurate-triacrylate, acrylizedepoxyoligomer, acrylates, acrylizedpolysiloxane	Heraeus Kulzer GmbH
Optiglaze	Og	Methyl methacrylate, multifunctional acrylate, silica filler, photo inhibitor	GC Corp
Biscover LV	Bc	Dipentaerythritolpentaacrylate, ethanol	Bisco Inc
Tab 2000	Tab	Methyl methacrylate, n-butylmethacrylate	Kerr Corp
Dentalon Plus	Dnt	Methacrylate, copolymer, peroxide, initiator, pigment	Heraeus Kulzer GmbH
Protempt 4	Prt	Ethanol,2,2'-[(1-methylethylidene bis(4,1 phenyleneoxy))] bis- diacetate,benzyl-phenyl- barbituric acid silane treated silica, tert-butyl	3 M ESPE
Tempofit	Tmp	Ethoxylated bisphenol A dimethacrylate	Detax

Table 2 Two-way ANOVA results for comparison of surface roughness (R_a) and bacterial adhesion (CFU/ml)

Parameter	Source	SS	df	MS	F	p
R_a	Interim material (A)	12.775	3	4.258	8.950	< 0.001*
	Surface treatment (B)	1.650	3	0.550	1.56	0.331
	A x B	14.919	9	1.658	3.484	0.001*
	Error	45.675	96	0.476		
	Total	468.137	112			
CFU/ml	Interim material (A)	60,067,676.670	3	20,022,558.890	152.179	< 0.001*
	Surface treatment (B)	2,594,065.955	3	864,688.652	6.572	< 0.001*
	A x B	7,002,976.509	9	778,108.501	5.914	< 0.001*
	Error	12,630,959.143	96	131,572.491		
	Total	217,765,083.000	112			

SS sum of squares; df degrees of freedom; MS mean square

* $P < 0.05$ indicates statistical significance

by a sanding machine (Phoenix Beta, Buehler) for 100 rev/min during 15 s, using 400 grit silicon carbide abrasive paper (Atlas Waterproof Sheet, Saint-Gobain). Control group specimens of each material were first polished using a slurry of coarse pumice (Isler Pomza, Isler Dental) and water with a bristle brush on a polishing lathe (P1000, Zubler) under standard pressure (for 90 s at a rate of 1500 rpm). Then, fine-polishing was achieved using a polishing paste (Universal Polishing Paste, Ivoclar Vivadent) and a lathe flannel wheel (Blaudent, Anka Dental) for 90 s. The specimens were coated with Palaseal,

Optiglaze, or BisCover LV with a soft brush in a thin, even layer in one direction to avoid air bubble formation. Then, the specimens were polymerized (Dentacolor XS, Heraeus Kulzer GmbH) at a reading of 750 mW/cm² for 90, 40, and 30 s, respectively.

Chewing simulation and surface roughness assessments

Surface roughness assessments were performed by using a contact profilometer (Perthometer M2, Mahr). Three measurements were made on each specimen by moving the diamond stylus (NHT- 6) of the device 5 mm in 7 s

Table 3 Mean R_{a0} and R_{a1} values (μ m), standard deviations (SD) and the statistical summaries of test groups

Interim Material	Surface Treatment	R_{a0}		R_{a1}		t-test** (P values)
		Mean (SD)	Tamhane*	Mean (SD)	Tamhane*	
Tab	Con	1.66 (0.39)	Cb	1.83 (0.37)	Aa	0.433
	Ps	0.31 (0.26)	Aa	1.35 (0.58)	Aa	0.002
	Og	0.52 (0.08)	ABa	2.29 (1.00)	Aa	0.004
	Bc	0.53 (0.15)	Aa	1.60 (0.44)	Aa	0.001
Dnt	Con	1.08 (0.26)	Bb	3.18 (0.64)	Bb	0.001
	Ps	0.32 (0.11)	Aa	1.91 (0.86)	Aa	0.003
	Og	0.40 (0.14)	ABa	2.50 (0.53)	Aab	0.001
	Bc	0.56 (0.18)	Aa	1.95 (0.46)	Aa	0.001
Prt	Con	0.74 (0.18)	Ab	0.91 (0.13)	Aa	0.066
	Ps	0.22 (0.09)	Aa	1.41 (0.64)	Aab	0.003
	Og	0.68 (0.24)	Bb	1.34 (0.71)	Aab	0.049
	Bc	0.47 (0.12)	Aab	2.12 (0.99)	Ab	0.004
Tmp	Con	0.81 (0.14)	Ab	1.88 (1.01)	Aa	0.030
	Ps	0.51 (0.18)	Aab	2.09 (0.54)	Aa	0.001
	Og	0.22 (0.11)	Aa	1.91 (0.53)	Aa	0.001
	Bc	0.48 (0.19)	Aab	1.70 (0.88)	Aa	0.010

*Statistical comparisons between interim material/surface treatment groups were shown as letters and values having same letters are not significantly different for Tamhane test ($p > 0.05$). The capital letters indicates the comparisons between same surface treatment applied interim material groups and the small caps indicates the differences between surface treatment groups for the same interim material

**The pairwise comparisons of R_{a0} and R_{a1} values with independent sample t-test ($P < 0.05$ indicates statistical significance)




Fig. 1 Scanning electron micrograph analysis after dynamic loading process ($\times 200$ magnification). Conventionally polished (A), Palaseal (B), Optiglaze (C), BisCover LV (D) coupled Tab 2000 interim crown materials

across the specimen's surface under constant pressure of 0.7 mN. The mean value of measurements obtained for each specimen was recorded as R_a0 value in μm .

All specimens were subjected to an aging process consisting computerized dynamic loading test in a multifunctional chewing simulator (Mod Chewing Simulator, Esetron) for 10,000 cycles at 50 N load combined with integral thermocycling (between 5 and 55 °C). The descending and ascending velocities were 60 mm/s and the loading cycle frequency was 1.6 Hz. The antagonist tooth was simulated by stainless steel spherical ball, 6 mm in diameter. Following chewing simulation, surface roughness of specimens were remeasured. The measurements were repeated three times for each specimen and the means obtained for each specimen were recorded as R_a1 .

Streptococcus mutans adhesion

Before bacterial adhesion, the specimens were cleaned with an ultrasonic cleaner (BioSonic; Coltène/Whaledent) for 15 min and sterilized in an autoclave at 121 °C for 15 min. Artificial saliva was prepared according to Fusayama formula: 0.4 g NaCl, 0.4 g KCl, 0.795 g CaCl_2 ($2\text{H}_2\text{O}$), 0.695 g $\text{Na}_2\text{H}_2\text{PO}_4$ (H_2O), 0.005 g Na_2S ($9\text{H}_2\text{O}$), 1 g $\text{CH}_4\text{N}_2\text{O}$ [25]. Specimens were covered

with artificial saliva and mucin suspension (M2378, Mucin from porcine stomach, Type II, Sigma Aldrich) (140 mg/100 ml) (5 ml) in a petri dish and left for 1 h to produce a pellicle [26, 27]. *Streptococcus mutans* NCTC 10,449 was used. and after rehydration of *Streptococcus mutans* strain in Tryptic Soy Broth (TSB, Oxoid), 100 μL of broth was transferred on to blood agar (Oxoid) and incubated in 5% CO_2 ambient air at 37 °C for 24 h. Then, tubes containing 2 ml of *Streptococcus mutans* suspension with 0.5 of McFarland turbidity (10^8 colony forming units/milliliter (CFU/ml)) were prepared in TSB (5% sucrose supplemented) and the incubated specimens in artificial saliva were transferred to those tubes. Tubes were incubated in same ambient conditions for 24 h. After incubation, the specimens were washed in sterile phosphate buffered saline (PBS) solution (8 gr NaCl, 0.2 g KCl, 1.44 g Na_2HPO_4 and 0.24 g KH_2PO_4 in 1000 ml of H_2O) by centrifuge at 1000 g for 3 min. After centrifugation, each specimen was placed in new glass tubes containing 1 ml of sterile PBS. The bacterial adhesion was evaluated by measuring colony-forming units per mL (CFU/ml). The tubes were treated for 6 min in an ultrasonic bath (50 kHz and 150 W), thereby the adherent bacteria cells were allowed to pass into the PBS. Three 1/10 serial dilutions were made in order to obtain




Fig. 2 Scanning electron micrograph analysis after dynamic loading process ($\times 200$ magnification). Conventionally polished (A), Palaseal (B), Optiglaze (C), BisCover LV (D) coupled Dentalon Plus interim crown materials (note rougher surface for conventionally polished specimen)

the lower quantity of bacteria in the sample. A 100 μ l of diluted PBS samples was sealed on blood agar and incubated in 5% CO₂ ambient at 37 °C for 24 h. At the end of incubation, the total number of adherent bacteria was calculated by multiplying the colonies observed counted with dilution coefficient.

Scanning electron microscopy (SEM) analysis

The surfaces of all resin materials after dynamic loading were examined with a scanning electron microscope (SEM) (Nova Nano SEM 450, FEI Co.). The acceleration voltage of cathode was set to 15 kV at a working distance of 9–10 mm and imaging was performed with $\times 200$, $\times 2000$ and $\times 5000$ magnifications. All images were examined by one observer.

Statistical analysis

The data were statistically analyzed by using a software program (SPSS version 19.0; SPSS Inc.). Kolmogorov-Smirnov test of homogeneity was used to evaluate the distribution of the variables. Surface roughness and bacterial adhesion data were analyzed with a 2-way ANOVA to evaluate the effects of surface treatment, resin type, and their interactions. The means were compared with

Tukey HSD test ($\alpha = 0.05$). Pearson correlation coefficient test was used to investigate the correlation between R_{a1} and bacterial adhesion values after dynamic loading, and $P < 0.05$ was considered significant.

Results

According to the 2-way ANOVA, for R_{a1} , the effect of interim material and interim material-surface treatment interaction was statistically significant ($P < 0.05$) (Table 2). Mean R_{a0} and R_{a1} values and standard deviations for interim material-surface treatment combinations are shown in Table 3. When conventionally polished material groups were compared, significant differences were observed for R_{a0} values of Tab and Dnt groups, and for R_{a1} values of Dnt group ($P < 0.05$).

For R_{a0} values, statistically significant differences were observed between the control and surface sealant applied specimens of all materials, except for Prt_Og, Prt_Bc, Tmp_Ps and Tmp_Bc ($P < 0.05$). Following dynamic loading, for R_{a1} values, statistically significant differences were found between Dnt control and Ps_Dnt and Bc_Dnt, and between Prt control and Prt_Bc ($P < 0.05$). Except for control groups of Tab and Prt, differences between R_{a0} and R_{a1} values were statistically




Fig. 3 Scanning electron micrograph analysis after dynamic loading process ($\times 200$ magnification). Conventionally polished (A), Palaseal (B), Optiglaze (C), BisCover LV (D) coupled Protemp 4 interim crown materials (note rougher surface for Biscover LV coupled specimen)

significant in all groups ($P < 0.05$). The R_a0 values (0.22 to 1.66 μm) and the R_a1 values (1.34 to 3.18 μm) for all groups were higher than the plaque accumulation threshold (0.20 μm). SEM images of the surfaces of Tab, Dnt, Prt, and Tmp after dynamic loading are shown in Figs. 1, 2, 3 and 4.

The interim material, surface treatment, and their interaction were statistically significant for bacterial adhesion ($P < 0.001$). Mean CFU/ml values, standard deviations (SD) and the statistical summaries for the interim material-surface treatment technique combinations are shown in Table 4. For all interim material groups, no statistically significant differences were observed between the control group and the surface sealant agent-coupled groups, except for Dnt_Bc ($P > 0.05$) (Fig. 5).

According to the Pearson Correlation Analysis, the coefficient of correlation between R_a1 and *Streptococcus mutans* adhesion was statistically significant ($P < 0.001$, $r^2 = 0.323$) and indicated that these two variables were moderately correlated (Table 5). SEM images of *Streptococcus mutans* adhesion and proliferation on rough surfaces are shown in Fig. 6.

Discussion

The first null hypothesis of this study was rejected because the effect of surface sealant agent coupling was significant on the surface roughness of some interim crown materials. Dynamic loading was significant on the surface roughness of interim crown materials except for control groups of Tab and Prt. Also, *Streptococcus mutans* adherence on interim crown materials was affected by dynamic loading. Accordingly, the second null hypothesis was rejected.

Rough surfaces lead to staining of the restoration, dental plaque formation, and the adhesion of oral microorganisms promotes tooth loss due to carious lesions and periodontal disease [8–15]. The increase in surface roughness promotes bacterial adhesion by increasing the contact area between the surface and microbial cells. Restorations with rough surfaces increase plaque accumulation by promoting the retention, survival and proliferation of *Streptococcus mutans*, which are considered to be one of the main pathogens involved in bacterial colonization and development of secondary caries, and many other microorganisms [28–30].




Fig. 4 Scanning electron micrograph analysis after dynamic loading process ($\times 200$ magnification). Conventionally polished (A), Palaseal (B), Optiglaze (C), BisCover LV (D) coupled Tempopit interim crown materials

In the present study, R_a values of interim crown materials ranged between 0.22 and 1.66 μm , which were below the clinical undetectability limit of 10 μm that Kaplan et al. [31] reported. However, these values are above the threshold R_a of 0.20 μm that Bollen et al. [32] indicated. Similar to the study findings of Ayuso-Montero et al. [8], the control groups of PMMA resins showed higher surface roughness values compared with the control groups of bis-acryl composite resins. Contrarily, unlike the findings of the present study, Şen et al. [3] reported that due to the heterogeneous composition of bis-acrylate composite resins, higher surface roughness values were observed with filler particles extruding on the surface.

Surface sealant agents applied to the surfaces of materials in a single phase are more advantageous than conventional polishing processes in terms of application and time. Surface sealant agents contribute to surface smoothness by filling the surface defects and micro cracks after application. However, due to their high viscosity, there are disadvantages such as weak bonding to the underlying material, degradation of surface quality, and low resistance to abrasion [18, 33]. In the present study, when the R_a values were evaluated, similar to

previous studies [18, 20], surface sealant agent application decreased the R_a values of all PMMA resin groups and bis-acryl resin groups, except Og- or Bc-coupled Prt and Pc- or Bc-coupled Tmp groups. Statistically significant differences observed in PMMA resins may have been due to increasing effect on the molecular weight of the components present on the surface of the methacrylate, and the decrease in surface roughness with the application of surface sealant agent. However, it has been shown that surface sealant agent application could remove surface particles that are not polymerized or adhered to the surface, causing surface irregularities. Also, application errors and the formation of air bubbles were reported to increase the R_a [19].

Due to intraoral conditions including chewing forces, nonpolymerized layer may be separated from the surface and micro-cracks may occur [21]. In the present study, dynamic loading was performed with multidirectional chewing simulator in order to evaluate the effect of oral environment on specimens prepared from interim crown materials. During dynamic loading, 6 mm diameter steatite, which has similar physical properties to enamel, was used as an antagonist

Table 4 CFU/ml values and statistical summaries of test groups

Interim material	Surface treatment	CFU/ml	
		Mean (SD)	Tamhane*
Tab	Con	177.14 (55.37)	Aa
	Ps	111.43 (41.81)	Aa
	Og	150.00 (41.53)	Aa
	Bc	99.29 (60.72)	Aa
Dnt	Con	2487.86 (348.59)	Cbc
	Ps	2887.14 (459.19)	Cc
	Og	1912.29 (563.62)	Cab
	Bc	1480.57 (621.02)	Ba
Prt	Con	980.00 (486.21)	Ba
	Ps	927.14 (340.13)	Ba
	Og	734.86 (430.32)	Ba
	Bc	1186.86 (638.34)	Ba
Tmp	Con	950.00 (92.60)	Ba
	Ps	1382.14 (172.60)	Ba
	Og	1114.29 (199.26)	Ba
	Bc	1015.71 (190.84)	Ba

*Statistical comparisons between interim material/surface treatment groups were shown as letters and values having same letters are not significantly different for Tamhane test ($P > 0.05$). The capital letters indicate the comparisons between same surface treatment applied interim material groups and the small letters indicate the differences between surface treatment groups for the same interim material

[34]. It is recommended that 240,000 chewing cycles should be performed to simulate 1 year of clinical service [22]. In the present study, 10,000 cycles corresponding to 15 days of clinical use were applied and after the dynamic loading process, it was observed that the surface roughness increased in all surface sealant agent coupled specimens. Also, SEM images of all resin groups after dynamic loading were consistent with the surface roughness measurements. This result may be attributed to the surface defects that occurred due to easy removal of the layer, potentially incompletely polymerized, on the surface of the resin, and to the low resistance of sealant agents to abrasion [21].

Streptococcus mutans has been reported to be the most abundant bacteria on enamel and root plaque (77%) [14], has high adhesion to all surfaces in the mouth, and it is a bacteria that is virulent with its acidogenic and aciduric properties [11]. Although in vitro studies have shown that artificial saliva does not reflect all the features of natural saliva [33], its use is essential for standardization [28, 35]. In the present study, to enable bacterial adhesion on the surface of the specimens, artificial saliva was prepared in accordance with the equation of Fusayama [33].

Similar to the findings of the present study, Aykent et al. [9] reported a positive correlation between the surface

Table 5 Correlation between R_a1 and bacterial colonisation

		R_a1	Colonisation
R_a1	Pearson correlation	1	0.323**
	Sig.		0.001
	N	112	112
Colonisation	Pearson correlation	0.323**	1
	Sig.	0.001	
	N	112	112

**Correlation is significant for $P < 0.01$ level

roughness and bacterial adhesion of restorative materials polished with different procedures. In the present study, SEM images (Fig. 6) revealed bacterial aggregation in areas with high surface roughness. Haralur et al. [36] compared stainless steel crowns, PMMA and bis-acryl resin interim crown materials, and the highest dental plaque accumulation was observed on PMMA specimens and the least was observed on the stainless-steel crown. Bacterial adhesion and proliferation on PMMA and bis acryl resin groups were reported to be due to hydrophilic polymer matrix and monomer structure. In the present study, the highest bacterial adhesion was found in the Dnt_Ps specimen group, while the least bacterial adhesion was in the Tab_Bc group.

Although surface roughness is an important feature in terms of bacterial adhesion, it is not a sufficient factor alone [6]. The effects of physical properties of materials such as surface electrical properties and free energy, hydrophobicity, fluoride release, as well as chemical properties have been previously studied [15]. Quirynen et al. [16] reported more dental plaque deposition on hydrophilic surfaces than on hydrophobic surfaces. Olsson et al. [15] stated that there was a critical limit on the hydrophobicity of surfaces in dental plaque deposition and the deposition below this limit would be minimal. Pellicle coating of the surfaces of dental materials changes the surface energy, which changes the bacteriostatic or bactericidal effect of the dental plaque [17]. Accordingly, these factors should be taken into consideration when interpreting the effects of varying factors and situations.

The specimens used in the current study were prepared in disc form containing flat surfaces, however, the recesses and protrusions on the tooth morphology may not allow an effective polishing process, and the roughness and bacterial adhesion may be affected. Clinical studies are needed to corroborate the findings of the present study. Also, further in vitro and in vivo research is needed to evaluate other factors affecting bacterial adhesion to interim materials particularly when surface sealants are used.




Fig. 5 Mean CFU values (CFU/ml) of test groups




Fig. 6 Scanning electron micrograph analysis after Streptococcus Mutans adhesion and proliferation (by two different magnifications, note aggregation on a rough surface). **A** 2000 × magnification; **B** 5000 × magnification

Conclusions

Within the limitations of this study, the following conclusions were drawn:

Even though surface sealant agent application significantly decreased the surface roughness compared with conventionally polished specimens, dynamic loading significantly increased the surface roughness of all

surface sealant coupled materials. R_a values of all test groups were higher than plaque accumulation threshold ($0.20 \mu m$). Streptococcus mutans adhered more on rougher surfaces. Although tested surface sealant agents enabled smoother surfaces, their use on occlusal surfaces of tested interim crown materials may lead to increased roughness compared with conventional polishing. When

Dentalon is used, Biscover LV application can be recommended for smoother surfaces with less bacterial adhesion.

Abbreviations

Bc: Biscover LV; BisGMA: Bisphenol glycidyl methacrylate; °C: Celsius; CFU/ml: Colony-forming unit/milliliter; Dnt: Dentalon Plus; mm: Millimeter; mN: MilliNewton; mm/s: Millimeter/seconds; ml: Milliliter; µl: Microliter; mW/cm²: Milliwatts/centimeter squared; N: Newton; Og: Optiglaze; PBS: Phosphate buffered saline; PEMA: Polyethyl methacrylate; PMMA: Poly (methyl methacrylate); Prt: Protemp 4; Ps: Palaseal; PVMA: Polyvinyl methacrylate; rpm: Revolutions per minute; Tab: Tab 2000; TEGDMA: Trimethylene glycol dimethacrylate; THFMA: Tetrahydrofurfuryl methacrylate; Tmp: Tempofit; SEM: Scanning electron microscopy; UDMA: Urethane dimethacrylate.

Acknowledgements

Not applicable.

Author contributions

E. E. T.: Methodology, investigation, resources, writing/ original draft, data acquisition. O. Ş.: Conceptualization, project administration, funding acquisition, validation, software, data curation. A. K.: Conceptualization, writing—review & editing. F. C.: Microbiologic studies and interpretation. B. Y.: Writing—review & editing, supervision. *All authors have read and approved the manuscript.

Funding

The authors thank to The Scientific Research Council of Zonguldak Bülent Ecevit University for financial support by "BEUN BAP 2015–33832697-04" numbered project.

Availability of data and materials

The datasets used and/or analysed during the current study are available from the corresponding author on reasonable request.

Declarations

Ethics approval and consent to participate

Not applicable.

Consent for publication

Not applicable.

Competing interests

The authors declare that they have no competing interests.

Author details

¹Sincan Oral Dental Health Center, 06930 Ankara, Turkey. ²Department of Prosthodontics, Faculty of Dentistry, Alanya Alaaddin Keykubat University, 07490 Antalya, Turkey. ³Department of Prosthodontics, Faculty of Dentistry, Zonguldak Bülent Ecevit University, 67600 Zonguldak, Turkey. ⁴Department of Microbiology, Faculty of Medicine, Zonguldak Bülent Ecevit University, 67600 Zonguldak, Turkey. ⁵Department of Reconstructive Dentistry and Gerodontology, School of Dental Medicine, University of Bern, 3012 Bern, Switzerland. ⁶Department of Restorative, Preventive and Pediatric Dentistry, School of Dental Medicine, University of Bern, 3012 Bern, Switzerland. ⁷Division of Restorative and Prosthetic Dentistry, The Ohio State University, Columbus, OH 43210, USA.

Received: 20 February 2022 Accepted: 7 July 2022

Published online: 19 July 2022

References

- Christensen GJ. The fastest and best provisional restorations. *J Am Dent Assoc.* 2003;134:637–9.
- Pery RD, Magnuson B. Provisional materials: key components of interim fixed restorations. *Compend Contin Educ Dent.* 2012;33:59–62.
- Şen D, Göller G, İşsever H. The effect of two polishing pastes on the surface roughness of bis-acryl composite and methacrylate-based resin. *J Prosthet Dent.* 2002;88:527–32.
- Luthardt RG, Stossel M, Hinz M, Vollandt R. Clinical performance and periodontal outcome of temporary crowns and fixed partial dentures: a randomized clinical trial. *J Prosthet Dent.* 2000;83:32–8.
- Turgut S, Bagis B, Ayaz EA, Ulusoy KU, Altintas SH, Korkmaz FM, et al. Discoloration of provisional restorations after oral rinses. *Int J Med Sci.* 2013;10:1503–9.
- Poggio C, Dagna A, Chiesa M, Colomco M, Scribante A. Surface roughness of flowable resin composites eroded by acidic and alcoholic drinks. *J Conserv Dent.* 2012;15:137–40.
- Krejci I, Lutz F, Boretti R. Resin composite polishing: filling the gap. *Quint Int.* 1999;30:490–5.
- Ayuso-Montero R, Martinez-Gomis J, Lujan-Climent M, Salsench J, Peraire M. Influence of matrix type on the surface roughness of three resins for provisional crowns and fixed partial dentures. *J Prosthodont.* 2009;18:141–4.
- Aykent F, Yondem I, Ozyesil AG, Gunal SK, Avunduk MC, Ozkan S. Effect of different finishing techniques for restorative materials on the surface roughness and bacterial adhesion. *J Prosthet Dent.* 2010;103:221–7.
- Bollen CML, Lambrechts P, Quirynen M. Comparison of surface roughness of oral hard materials to the threshold surface roughness for bacterial plaque retention: a review of the literature. *Dent Mater.* 1997;13:258–69.
- Kawai K, Urano M. Adherence of plaque components to different restorative materials. *Oper Dent.* 2001;26:396–400.
- Quirynen M, Marechal M, Busscher HJ, Weerkamp AH, Darius PL, van Steenberghe D. The influence of surface free energy and surface roughness on early plaque formation: an in vivo study in man. *J Clin Periodontol.* 1990;17:138–44.
- Carlen A, Nikdel K, Wennerberg A, Holmberg K, Olsson J. Surface characteristics and in vitro biofilm formation on glass ionomer and composite resin. *Biomaterials.* 2000;22:481–7.
- Nyvad B, Kilian M. Comparison of the initial streptococcal microflora on dental enamel in caries-active and in caries-inactive individuals. *Caries Res.* 1990;24:267–72.
- Olsson J, van der Heijde Y, Holmberg K. Plaque formation in vivo and bacterial attachment in vitro on permanently hydrophobic and hydrophilic surfaces. *Caries Res.* 1992;26:428–33.
- Quirynen M, Marechal M, Busscher HJ, Weerkamp AH, Arends J, Darius PL, van Steenberghe D. The influence of surface free energy on planimetric plaque growth in man. *J Dent Res.* 1989;68:796–9.
- Quirynen M, Bollen CM. The influence of surface roughness and surface-free energy on supra- and subgingival plaque formation in man: a review of the literature. *J Clin Periodontol.* 1995;22:1–14.
- Borchers L, Tavassol F, Tschernitschek H. Surface quality achieved by polishing and by varnishing of temporary crown and fixed partial denture resins. *J Prosthet Dent.* 1999;82:550–6.
- Bertrand MF, Leforestier E, Muller M, Lupi-Pegurier L, Bolla M. Effect of surface penetrating sealant on surface texture and microhardness of composite resins. *J Biomed Mater Res.* 2000;53:658–63.
- Köroğlu A, Şahin O, Dede DÖ, Yılmaz B. Effect of different surface treatment methods on the surface roughness and color stability of interim prosthodontic materials. *J Prosthet Dent.* 2016;115:447–55.
- Doray PG, Eldiwany MS, Powers JM. Effect of resin surface sealers on improvement of stain resistance for a composite provisional material. *J Esthet Restor Dent.* 2003;15:244–50.
- Ho TK, Satterthwaite JD, Silikas N. The effect of chewing simulation on surface roughness of resin composite when opposed by zirconia ceramic and lithium disilicate ceramic. *Dent Mater.* 2018;34:e15–24.
- Heintze SD. How to qualify and validate wear simulation devices and methods. *Dent Mater.* 2006;22:712–34.
- Chitmongkolsuk S, Heydecke G, Stappert C, Strub JR. Fracture strength of all-ceramic lithium disilicate and porcelain-fused-to-metal bridges formolar replacement after dynamic loading. *Eur J Prosthodont Rest Dent.* 2002;10:15–22.
- Lassila LV, Vallittu PK. Effect of water and artificial saliva on the low cycle fatigue resistance of cobalt-chromium dental alloy. *J Prosthet Dent.* 1998;80:708–13.

26. Blake-Haskins JC, Mellberg JR, Synder C. Effect of calcium in model plaque on the anticaries activity of fluoride in vitro. *J Dent Res*. 1992;71:1482–6.
27. Lewinstein I, Furher N, Gelfand K, Cardash H, Pilo R. Marginal leakage and cement solubility of provisional crowns cemented with temporary cement containing stannous fluoride. *Int J Prosthodont*. 2003;16:186–93.
28. Eick S, Glockmann E, Brandl B, Pfister W. Adherence of *Streptococcus mutans* to various restorative materials in a continuous flow system. *J Oral Rehabil*. 2004;31:278–85.
29. Brandão NL, Portela MB, Maia LC, Antônio A, Silva VLME, Silva EMD. Model resin composites incorporating ZnO-NP: activity against *S mutans* and physicochemical properties characterization. *J Appl Oral Sci*. 2018;26:1–10.
30. Ionescu AC, Cazzaniga G, Ottobelli M, Ferracane JL, Paolone G, Brambilla E. *In vitro* biofilm formation on resin-based composites cured under different surface conditions. *J Dent*. 2018;77:78–86.
31. Kaplan BA, Goldstein BR, Vijayaraghavan TV, Nelson IK. The effect of three polishing systems on the surface roughness of four hybrid composites: a profilometric and scanning electron microscopy study. *J Prosthet Dent*. 1996;76:34–8.
32. Bollen CML, Papaioanno V, Van Eldere J, Schepers E, Quirynen M, Van Steenberghe D. The influence of abutment surface roughness on plaque accumulation and peri-implant mucositis. *Clin Oral Implants Res*. 1996;7:201–11.
33. Gal JY, Fovet Y, Yadzi MA. Review about a synthetic saliva for in vitro studies. *Talanta*. 2000;53:1103–15.
34. Wassel RW, McCabe JF, Walls AW. A two-body frictional wear test. *J Dent Res*. 1994;73:1546–53.
35. Andrysewicz E, Mystkowska J, Kolmas J, Jalbrzykowski M, Olchowik R, Dabrowski JR. Influence of artificial saliva compositions on tribological characteristics of ti-6Al-4V implant alloy. *Acta Bioeng Biomech*. 2012;14:71–9.
36. Haralur SB, Gana SN, Aldowash OS, Al-Hytham A. Quantitative evaluation on the ability of dental plaque adherence to commonly used provisional crowns. *J Int Oral Health*. 2012;4:17–22.

Publisher's Note

Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.

Ready to submit your research? Choose BMC and benefit from:

- fast, convenient online submission
- thorough peer review by experienced researchers in your field
- rapid publication on acceptance
- support for research data, including large and complex data types
- gold Open Access which fosters wider collaboration and increased citations
- maximum visibility for your research: over 100M website views per year

At BMC, research is always in progress.

Learn more biomedcentral.com/submissions

